

## SIENA QUARTZ Specifications + Performance



## SPECIFICATIONS

| Collection:  | Siena               |
|--------------|---------------------|
| Price Grade: | Vogue III           |
| Finish:      | polished or honed   |
| Thickness:   | 1.5/2/3cm           |
| Application: | indoors             |
| Composition: | ≤ 90% quartz, resin |



| PERFORMANCE TEST                                | METHOD                 | RESULT                         |
|---|------------------------|--------------------------------|
| Abrasion resistance                             | ASTM C1353/C1353M-20°1 | 104.38                         |
| Breaking strength                               | ASTM C648-20           | 15206N                         |
| Absorption and bulk apositic gravity            | ASTM C97/C97M-18       | Absorption: 0.02%              |
| Absorption and bulk specific gravity            |                        | Density: 2367kg/m <sup>3</sup> |
| Thermal shock resistance of glazed ceramic tile | Refer to ASTM C484-20  | No visible defects             |
| Resistance to chemical substances               | ASTM C650-20           | Not affected                   |
| Apparent gravity                                | Refer to ASTM C373-18  | 2.37 g/cm <sup>3</sup>         |
| Moh's hardness                                  | Refer to EN 15771:2010 | See the following              |
| Thermal expansion                               | ASTM C531-00(2012)     | 43.0x10 <sup>-6</sup> /°C      |
| Flexural strength                               | ASTM C880/C880M-18     | Dry: 48.1Mpa                   |
|   |                        | Wet: 63.7MPa                   |
| Modulus of rupture                              | ASTM C99/C99M-18       | Dry: 57.1MPa                   |
|   | V21M C22/C22M-T0       | Wet: 68.7MPa                   |
| Moh's hardness                                  | 6                      |                                |